

## syntha pulvin matt

<b>Chemical type:</b>	Superdurable Polyester
<b>Product details:</b>	Meets requirements of BS6496:1984 and BS6497:1984 Approved to Qualicoat Class 1(P-0139) and GSB (129c) Superior outdoor durability and colour retention Available from stock in BS and RAL colours
<b>Application:</b>	Electrostatic and Tribo
<b>Particle size:</b>	3% maximum > 120µm 10% maximum < 10µm 34-42µm average size
<b>Curing:</b>	15 mins @ 190°C (metal temperature) 10 mins @ 200°C (metal temperature) 8 mins @ 210°C (metal temperature)
<b>Gloss level:</b>	30 +/- 5 units (60° head glossmeter)
<b>Film thickness:</b>	60-120µm, typically 80µm
<b>Shelf life:</b>	12 months in cool, dry conditions
<b>Health and Safety:</b>	Refer to Material Safety Data Sheet from Valspar

### Product performance:

It is essential to pretreat architectural components prior to application of Syntha Pulvin matt. Detailed advice should be sought from the pretreatment supplier. Aluminium components should receive a multi-stage chromate conversion coating. Galvanised steel should receive a multi-stage pretreatment using either chromate or zinc phosphate. De-gassing of galvanised steel prior to powder application is considered mandatory.

The following tests were all carried out on 0.8mm chromated aluminium test panels having a nominal coating thickness of 60µm.

TEST	UK SPECIFICATION	ISO/ASTM SPECIFICATION
Cross hatch adhesion	BS3900 E6 – class 0	ISO 2409 – pass Gt0
Impact resistance	BS6496 – pass 20 “lbs	ASTM D 2794 – pass 2.5Nm
Flexibility	BS3900 E11 – pass 6mm	ISO 1519 – pass 6mm
Cupping test	BS3900 E4 – pass 8mm	ISO 1520 – pass 8mm
Scratch/Hardness	BS3900 E2 – pass 4kg	ISO 1518 – pass 4kg
Acetic Acid salt spray resistance	BS6496 (15) – pass 1000 hours	ISO 9227 – pass 1000 hours
Humidity resistance	BS3900 F2 – pass 1000 hours	ASTM D2247 – pass 1000 hours
Artificial weathering	B3900 F16 –Pass 1000 hours	ISO 11507 pass 1000 hours
Natural weathering (Florida 45°)	Pass 1 year – minimal colour change, gloss retention> 50%	
Chemical resistance	Resistant to most acids, alkalis and oils at normal temperatures. May be affected by chlorinated solvents.	

*Whilst we endeavour to ensure all advice is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability arising from the use or performance of the product in service.*